


Electrodeposited copper foil designed for lithium-ion battery and other power storage applications. Topography on both sides of foil for added adhesion.

Applications:


- Lithium Ion Batteries

Features:

- IPC Grade I
- No oils or organic coatings
- Treatment applied to drum side to aid in coating adhesion
- Available up to 1346 mm (53") wide



Treated Drum Side
H oz. /18 µm (1500x)



Untreated Matte Side
H oz. /18 µm (1500x)

Typical Values:

Attribute		Unit	Value				Reference
Thickness Designation			Q	N/A	T	H	IPC-4562, 1.2.5.1 Table 1-1; IPC-TM-650-2.2.12
Nominal Thickness		µm	9	10	12	18	
		oz.	1/4	2/7	3/8	1/2	
Area Weight		g/m ²	75.9	88.9	106.8	152.5	
		g/254 in ²	12.5	14.6	17.5	25	
		oz./ft ²	0.25	0.292	0.375	0.5	
Roughness	Drum Side	µm	2.54				IPC-TM-650-2.2.17
		µ"	100				
	Matte Side	µm	2.92		3.05	3.68	
		µ"	115		120	145	
Tensile	Ambient	Kg/mm ²	42				IPC-TM-650-2.4.18
		Kpsi	60				
Elongation	Ambient	%	4		7	10	

Information in this document is believed to be accurate and reliable and is for informational purpose only. This data sheet does not create any warranties, expressed or implied, as to the fitness for any particular purpose or use. The Denkai America Inc. name and logo are registered trademarks of Nippon Denkai, Ltd. © 2020, Denkai America Inc. All rights reserved. Rev May 4, 2020