


High reliability electrodeposited copper foil.

Applications:


- Resistive layers

Features:

- IPC Grade III
- Treatment on matte side of foil
- Designed for use in resistive layers



Untreated Drum Side
H oz. /18 μm (1500x)



Treated Matte Side
H oz. /18 μm (1500x)

Typical Values:

Attribute		Unit	Value			Reference
Thickness Designation			T	H	1	IPC-4562, 1.2.5.1 Table 1-1; IPC-TM-650-2.2.12
Nominal Thickness		μm	12	18	35	
		oz.	3/8	1/2	1	
Area Weight		g/m ²	106.8	152.5	305	IPC-TM-650-2.2.17
		g/254 in ²	17.5	25	50	
		oz./ft ²	0.375	0.5	1	
Roughness	Drum Side	μm	0.25	0.25	0.25	IPC-TM-650-2.4.18
		μ"	10	10	10	
	Matte Side	μm	5.08	6.35	7.62	
		μ"	200	250	300	
Tensile	Ambient	Kg/mm ²	42.2	42.2	38.7	IPC-TM-650-2.4.18
		Kpsi	60	60	55	
	180°C	Kg/mm ²	21.1	21.1	21.1	
		Kpsi	30	30	30	
Elongation	Ambient	%	6	8	15	
	180°C	%	8			

Information in this document is believed to be accurate and reliable and is for informational purpose only. This data sheet does not create any warranties, expressed or implied, as to the fitness for any particular purpose or use. The Denkai America Inc. name and logo are registered trademarks of Nippon Denkai, Ltd. © 2020, Denkai America Inc. All rights reserved. Rev May 4, 2020