


Reverse treat electrodeposited copper foil.

Applications:


- PCB inner layers

Features:

- IPC Grade III
- Treatment on drum side of foil
- Excellent adhesion to a wide range of resin systems



Treated Drum Side
H oz. /18 µm (1500x)



Untreated Matte Side
H oz. /18 µm (1500x)

Typical Values:

Attribute		Unit	Value						Reference
Thickness Designation			Q	T	H	1	2	3	IPC-4562, 1.2.5.1 Table 1-1; IPC-TM-650-2.2.12
Nominal Thickness		µm	9	12	18	35	70	103	
		oz.	1/4	3/8	1/2	1	2	3	
Area Weight		g/m ²	75.9	106.8	152.5	305	610	915	
		g/254 in ²	12.5	17.5	25	50	100	150	
		oz./ft ²	0.25	0.375	0.5	1	2	3	
Roughness	Drum Side Ra	µm	3.0						IPC-TM-650-2.2.17
		µ"	120						
	Matte Side Rz	µm	2.5	3.2	4.5	5.7	8.9	14.5	
		µ"	100	125	175	225	350	570	
Tensile	Ambient	Kg/mm ²	42			38.7	36.9	34.7	IPC-TM-650-2.4.18
		Kpsi	60			55	52.5	49.3	
	180°C	Kg/mm ²	21						
		Kpsi	30						
Elongation	Ambient	%	>3	6	8	15	20	25.5	
	180°C	%	8						
Peel Strength* (Drum/Treated Side)	Cond. B	Kg/cm	>0.89	1.07	1.07	1.42	1.96	2.5	IPC-TM-650-2.4.8
		Lbs/in	>5.0	6	6	8	11	14	

* Peel strength measured on 170°C Tg Epoxy

Information in this document is believed to be accurate and reliable and is for informational purpose only. This data sheet does not create any warranties, expressed or implied, as to the fitness for any particular purpose or use. The Denkai America Inc. name and logo are registered trademarks of Nippon Denkai, Ltd. © 2020, Denkai America Inc. All rights reserved. Rev May 4, 2020